



# TEST REPORT

No. : CT10-15727-A1

Customer Name : ERGOTECH CO., LTD

Date of Test : Apr. 01, 2010

Address : #292-2, Shinhyeonri Opoeup Gwngjusi Gyeonggi-do Korea

Receipt Date : Mar. 26, 2010

Test Sample : Super Safe Mat

## Test Results

Items	Units	Results	Test Methods
Specific gravity	-	1.18	KS M 6519:2008
Hardness (Hs : Shore A Type)	-	49	KS M 6518:2006
Tensile strength (Specimen : Dumbbell No.3)	MPa	9.1	
Elongation	%	740	
Tear strength (Specimen : B Type)	kN/m	15	

Our report apply only to the standards or procedures identified and to sample(s) tested unless otherwise specified. The test results are not indicative of representative of the qualities of the lot from which the sample was taken or of apparently identical or similar products.

- End of Report -

Tested  
by

Joon Young Heo

J. Y. Heo

Technical  
Manager

Young Hwa Kim

Y. H. Kim

Apr. 01, 2010

Korea Environment &amp; Merchandise Testing Institute

President Chang Ro Kim

Kim Chang Ro

Address : 153-803 459-28, Gasan-Dong, Geumcheon-Gu, Seoul, Korea 82-2-2102-2500

Result Inquiry : Polymer Testing Department 82-2-2102-2661~2666

www.kemti.org